

ACRYLITE® Film 0F016

Product Data Sheet

Product

ACRYLITE® Film 0F016 is a high weather resistant, glossy and transparent acrylic film for graphic printings and high quality laminations.

Due to its excellent performance under weathering and UV light exposure, ACRYLITE® Film 0F016 does not present color change or yellowing. Therefore it provides high protection of laminating systems from degradation caused by UV radiation.

Its glossy and very smooth surface leads the film to have an excellent optical quality surface.

Application

ACRYLITE® Film 0F016 can be used to be printed on as high quality film decoration and then laminated on different polymeric films and sheets. Laminated decoration films based on ACRYLITE® are suitable for a wide range of molding processes such as thermoforming, and insert molding.

In labels and tapes, ACRYLITE® Film 0F016 can be used as single face layer or clear overlay in laminate systems for high UV and weathering protection. High gloss and quality finishing is achieved.

Due to its good optical property and lamination with pressure sensitive adhesive (PSA), ACRYLITE® Film 0F016 is recommended for traffic control signs under long term outdoor application.

Due to its very good optical properties, ACRYLITE® Film 0F016 can be used as overlay in high quality ID Cards.

Processing

ACRYLITE® Film 0F016 has a good printability behavior in all printing technologies such as gravure, flexography and digital. In most of the cases any pre-treatment or primers are not required.

ACRYLITE® Film 0F016 can be laminated onto polymeric substrates such as films or extruded sheets based on PVC, PC, ABS, PMMA and ASA by in-line or roll-to-roll heat lamination.

High quality laminates in between ACRYLITE® Film 0F016 and other polymeric substrates such as PET, PC, PP, PE and PVC can be achieved with pressure sensitive adhesives (PSA) or solvent based adhesives.

The film can be cut-to-size or die cut.

Sales range

ACRYLITE® Film 0F016 is delivered in standard rolls of 60 or 75µm thickness, 1270mm width, and 1000mm length.

Tailor made rolls can be produced under prior commercial agreement.

Technical data

Properties	Test method	Unit	Value
Optical			
Luminous transmittance τ_{D65}	ISO 13468-2	%	92
UV transmittance (280 - 380 nm)	DIN EN 410:2011	%	< 1
Refractive Index	ISO 489	%	1,49
Mechanical			
Tensile stress at yield (σ_y)	ISO 527-3	MPa	47
Yield strain (ϵ_y)	ISO 527-3	%	6
Nominal strain at break (ϵ_b)	ISO 527-3	%	> 25
Thermal			
Glass transition temperature T_g (DSC)	ISO 11357	°C	101
Miscellaneous			
Accelerated weathering resistance	ISO 4892-2 method A, cycle 1, 65% RH	h	8000 No visible changes
Specific gravity	DIN 53479	g/cm ³	1,15
Surface tension	DIN 53364	mN/m	50

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether expressed or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technical progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products should be used.

Evonik Industries is a worldwide manufacturer of PMMA products sold under the ACRYLITE® trademark in the Americas and under the PLEXIGLAS® trademark in the European, Asian, African, and Australian continents. ©Evonik Cyro LLC. All rights reserved.

Printed in the USA.

Evonik Cyro LLC
 299 Jefferson Road, Parsippany, NJ 07054 US
 Phone +1 800 631 5384
 films@evonik.com www.acrylite.net